



LEADERS IN WAX TECHNOLOGY

THE FINEST NATURAL WAXES IN THE WORLD SINCE 1904

DATA SHEET

ALL NATURAL CANDLE BLENDS

S & P Number	Name	Description	Melting Point ASTM D-127	Congeaing Point ASTM D-938	Needle Penetration ASTM D-1321 @ 77°F
SP-470	All Natural crystalline pillar blend	A combination of natural waxes, providing a good clean burn expected of natural wax candles.	130°F – 140°F		4-12
SP-483P	All natural smooth pillar blend.	Smooth and Creamy texture easy to burn and handles like paraffin.	132°F	130°F	18
SP-486P	All natural free standing candle blend.	Hard crystalline texture, exceptional mold release, excellent fragrance loading capacity.	143°F	130°F	4
SP-487P	All natural container candle blend.	Hard crystalline texture, very good adhesion to the glass, excellent fragrance loading capacity.	131°F	126°F	8
SP-488	All natural smooth container blend.	Smooth & creamy texture easy to burn & handles like paraffin.	135°F	130°F	33